

ACRYLIC™ INK

155 BISMUTH YELLOW PY184 □ ☼	159 CADMIUM YELLOW LIGHT HUE PY138 □ ☼	412 YELLOW MEDIUM AZO PY74 □ ☼	414 YELLOW ORANGE AZO PY83 □ ☼	295 YELLOW DEEP PY74 • P067 □ ☼	298 YELLOW ORANGE PY74 • P067 ■ ☼	720 BRIGHT ORANGE P073 ■ ☼	620 VIVID RED ORANGE PRI88 □ ☼
294 NAPHTHOL RED LIGHT PRI12 ■ ☼	321 PYRROLE RED PR254 □ ☼	292 NAPHTHOL CRIMSON PRI70 □ ☼	507 PERYLENE MAROON PRI79 □ ☼	388 RUBINE RED PRI84 ■ ☼	114 QUINACRIDONE MAGENTA PRI22 □ ☼	115 DEEP VIOLET PRI12 • PV23 RS ■ ☼	015 PURPLE PRI22 • PV23 □ ☼
391 PRISM VIOLET PRI22 • PV23 □ ☼	186 DIOXAZINE PURPLE PV23 RS □ ☼	314 PHTHALOCYANINE BLUE red shade PB15:3 • PV23 □ ☼	320 PRUSSIAN BLUE HUE PB15:3 • PV23 RS • PBk7 □ ☼	316 PHTHALOCYANINE BLUE green shade PB15:3 □ ☼	470 CERULEAN BLUE HUE PW6 • PB15:3 • PG7 ■ ☼	287 TURQUOISE PB15:3 • PG7 □ ☼	561 TURQUOISE DEEP PB15:3 • PG7 □ ☼
317 PHTHALOCYANINE GREEN blue shade PG7 □ ☼	319 PHTHALOCYANINE GREEN yellow shade PG36 □ ☼	224 HOOKER'S GREEN HUE PERMANENT PY83 • PG7 • PBk7 □ ☼	315 SAP GREEN PERMANENT PG7 • PY83 • PBk7 ■ ☼	740 VIVID LIME GREEN PY138 • PG7 □ ☼	416 YELLOW OXIDE PY42 ■ ☼	332 TRANSPARENT RAW SIENNA PY42 □ ☼	335 RED OXIDE PRI01 ■ ☼
129 TRANSPARENT BURNT SIENNA PRI01 □ ☼	130 TRANSPARENT BURNT UMBER PRI01 • PBk7 □ ☼	333 TRANSPARENT RAW UMBER PY42 • PRI01 • PBk7 □ ☼	609 SEPIA PRI01 • PRI79 • PBk7 □ ☼	432 TITANIUM WHITE PW6 ■ ☼	599 NEUTRAL GRAY 5 PW6 • PBk7 ■ ☼	337 CARBON BLACK PBk7 ■ ☼	236 IRIDESCENT BRIGHT SILVER ■ ☼
234 IRIDESCENT BRIGHT GOLD ■ ☼	227 IRIDESCENT ROSE GOLD ■ ☼	229 IRIDESCENT RICH BRONZE ■ ☼	230 IRIDESCENT RICH COPPER ■ ☼	987 FLUORESCENT PINK □ ☼	983 FLUORESCENT RED □ ☼	982 FLUORESCENT ORANGE □ ☼	981 FLUORESCENT YELLOW □ ☼
985 FLUORESCENT GREEN □ ☼	984 FLUORESCENT BLUE □ ☼	504 MUTED PINK PY42 • PRI22 • PV23 □ ☼	502 MUTED VIOLET PRI22 • PBk7 □ ☼	505 MUTED GREY PY42 • PB15:3 • PV23 □ ☼	503 MUTED TURQUOISE PV23 • PB15:3 • PG7 • PBk7 □ ☼	501 MUTED GREEN PV23 • PG36 □ ☼	

55
COLORS

KEY TO CODING

OPACITY RATING

- Opaque
- ☼ Semi-Opaque
- Transparent

ASTM LIGHTFASTNESS RATING

- ☼ Excellent
- ☼ ☼ Very good
- ☼ Not ASTM rated